

# THE CROWN OF POWER SOLUTION

#### **GEL Deep Cycle Battery**

PS-121500-GS [12V150Ah]



#### 🔗 General Features

- Designed floating charging service life: 15 years (25°C)
- · Safety valve installation for explosion proof ,Sealed and maintenance free operation
- By using strong grids, high purity lead and patented Gel electrolyte
- Extremely low self-discharge characteristic
- Wide operating temperature range from -20°C~55°C
- Lead Aluminum calcium Tin alloy high energy, prevent corrosion

# **Application**

- DC power supply
- UPS/EPS power supplyElectrical devices & instruments

• Security and fire alarm systems


- Medical equipments
  - Emergency lighting systems

Telecom stations and power stations

## Figure 2 Physical Specifications

Nominal Voltage	Nominal Capacity (10HR)		Dime	nsion		Internal	Standard	
		L	W	Н	TH	Weight ±3%	Resistance (In full charge status)	Terminals
12V	150AH	485±3mm	170±2mm	240±3mm	240±3mm	Approx 44.3kg (97.46lbs)	≈3.10mΩ	T23 (standard)

# X Dimensions



# E Constant-Voltage Charge


Rated Capacity		Cycle Application						
20 hour rate (7.5A)	154.5AH	1. Limit initial current less than 37.5A.						
10 hour rate (15.0A)	151.0AH	2. Charge until battery voltage (under charge) reaches 14.1V to 14.4V at 25°C(77°F)						
5 hour rate (25.5A)	127.5AH	3. Hold at 14.1V to 14.4V until current drop to under0.90A for at least 3 hours.						
3 hour rate (37.5A) 114.0AH		4. Temperature compensation coefficient of charging voltage is -30mV/ºC.						
1 hour rate (90.0A) 90.0AH		Standby Service						
Capacity affected by	Temperature	1. Hold battery across constant voltage source of 13.6 to 13.8 volts with current limit <i>37.50</i> A continuously .When held at this voltage , the battery will seek its own current level and maintain itself in a fully charge status.						
40°C(104°F)	103%							
25°C(77°F)	100%							
0°C(32°F) 86%		2. Temperature compensation coefficient of charging voltage is -18mV/ºC.						


A NOTE : The battery should be charged within 6 months of storage, Otherwise, permanent loss of capacity might occur as a result of sulfation


# **Battery Discharge Table**


End	Minute (M)				Hour (H)								
Voltage (V)	5	10	15	30	45	1	1.5	2	3	5	8	10	20
Constant Current Discharge Data Sheet (Amperes at 25°C)													
10.20	472	360	271	144	133	93.6	73.9	61.9	38.8	26.95	19.17	15.88	8.03
10.50	419	330	253	138	127	89.9	71.0	59.7	37.5	25.73	18.13	15.58	7.95
10.80	389	300	237	133	121	86.1	68.1	57.3	36.2	24.62	17.23	15.13	7.85
Constant Power Discharge Data Sheet (Watt at 25°C)													
10.20	4695	3975	2861	1797	1350	1173	855	644	480	310	230	195	102.2
10.50	4515	3375	2568	1756	1320	1155	842	623	465	300	227	189	99.0
10.80	4200	3150	2452	1718	1275	1103	804	602	449	289	224	180	96.8


## **Performance Characteristics**














Info@powersolid.vn www.powersolid.vn
wyw.powersolid.vn
wyw.pow

